

## Historic, archived document

Do not assume content reflects current  
scientific knowledge, policies, or practices





1.8  
EX892E



# SOME GRADES OF WOOL


Samples shown are actual lengths



COMBING LENGTH

4147-C

TWO SAMPLES OF FINE WOOLS  
Equivalent to U. S. fine grades



CLOTHING LENGTH

4152-D

BRAID WOOL  
Equivalent to U. S. braid grades



COMBING LENGTH


4145-C



COMBING LENGTH

4143-C

QUARTER-ELOOD WOOLS  
Equivalent to U. S. quarter-blood grades



CLOTHING LENGTH

33548-B

Fine wool, combing length is used for fine worsteds, very fine serges, dress materials, and lansdowns.  
Fine wool, clothing length is used for fine woolens, broadcloth, felts, underwear, and flannels.  
Quarter-blood wool, combing length is used for medium serges, worsted goods, and knitting yarns.  
Quarter-blood wool, clothing length is used for medium grade woolens and blankets.  
Braid wool is used for homespun, carpets, and plushes.

Prepared by Extension Service, in cooperation with the Bureaus of Animal Industry and Agricultural Economics,  
United States Department of Agriculture, Washington, D. C.

Group No. 4.—Sheep, Goats, Wool, and Mohair (Chart No. 4.3). Group of three charts. Price 15 cents. Issued 1928, revised 1939.